

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application and reflects the amendment of claims 1, 5, 6, 8, 12-15, 17, 18, 20, 24-26 and 31; the cancellation of claims 11 and 23; and the addition of new claims 38-46.

Listing of Claims:

1. (Currently amended) Method for reducing emissions of one or more gaseous substances, emitted from an exposed glue line of ~~from an assembly of at least two pieces of wooden materials which have been glued together, the one or more gaseous substances belonging to the group of aldehydes and-or isocyanates, comprising planing on-at least one of the sides having glue lines exposed, followed by treating the at least one planed sides~~ by application of a liquid treating composition containing ~~with one or more treating substances reactive to an aldehyde or an isocyanate the one or more gaseous substances.~~

2. (Cancelled)

3. (Cancelled)

4. (Cancelled)

5. (Currently amended) Method according to claim-~~14~~ 1, wherein one gaseous substance is formaldehyde.

6. (Currently amended) Method according to claim-~~14~~ 1, wherein one treating substance is urea or a urea derivative.

7. (Cancelled)

8. (Currently amended) Method according to claim-~~17~~ 1, wherein one treating substance is a reaction product of an alcohol and ammonia.

9. (Cancelled)

10. (Cancelled)

11. (Cancelled)

12. (Currently amended) Method according to claim 1 ~~14~~, wherein the treating composition comprises from about 1 to about 80 weight % of the one or more treating substances.

13. (Currently amended) Method according to claim 1 44, wherein the treating composition comprises from about 0.02 to about 10 weight % of a polymer.

14. (Currently amended) Method according to claim 1 44, wherein the treating composition comprises a polyvinylalcohol dispersion.

15. (Currently amended) Method for producing a laminated wooden product comprising the steps of:

- (a) - applying an adhesive system onto one or more wooden lamellas,
 - (b) - assembling two or more wooden lamellas into an assembly,
 - (c) - pressing the assembly,
 - (d) - planing at least one of the sides of the assembly having glue lines exposed,
- and,
- (e) - treating the one or more planed sides by application of a liquid treating composition containing one or more treating substances reactive to an aldehyde or an isocyanate ~~one or more gaseous substances~~ emitted from the at least one planed side.

16. (Cancelled)

17. (Currently amended) Method according to claim 1546, wherein one gaseous substance is formaldehyde.

18. (Currently amended) Method according to claim 15 3546, wherein one treating substance is urea or a urea derivative.

19. (Cancelled)

20. (Currently amended) Method according to claim 1549, wherein one treating substance is a reaction product of an alcohol and ammonia.

21. (Cancelled)

22. (Cancelled)

23. (Cancelled)

24. (Currently amended) Method according to claim 15 23, wherein the treating composition comprises from about 1 to about 80 weight % of the one or more treating substances.

25. (Currently amended) Method according to claim 15 23, wherein the treating composition comprises from about 0.02 to about 10 weight % of a polymer.

26. (Currently amended) Method according to claim 15 23, wherein the treating composition comprises a polyvinylalcohol dispersion.

27. (Original) Method according to claim 15, wherein the laminated wooden product is a laminated beam.

28. (Cancelled)

29. (Cancelled)

30. (Cancelled)

31. (Currently amended) Method for reducing emissions of gaseous substances from a glued laminate, comprising the steps of:

(1) gluing together a plurality of ~~laminates~~ lamellas with an adhesive substance capable of emitting at least one gaseous substance being an aldehyde or an isocyanate, thereby forming a laminated beam having exposed glue lines on at least one side thereof and from which said at least one gaseous substance can be emitted;

(2) planing said at least one side having exposed glue lines; and

(3) treating the at least one planed side by application of a liquid treating composition containing ~~with~~ one or more treating substances reactive to an aldehyde or an isocyanate ~~said one or more gaseous substances~~, thereby reducing or eliminating the emission of the aldehyde or the isocyanate ~~said at least one gaseous substance~~.

32. (Previously Presented) Method according to claim 1, wherein one treating substance contains an amino or amide group.

33. (Previously Presented) Method according to claim 1, wherein one treating substance is a sulphite.

34. (Previously Presented) Method according to claim 1, wherein one treating substance is an alcohol.

35. (Previously Presented) Method according to claim 15, wherein one treating substance contains an amino or amide group.

36. (Previously Presented) Method according to claim 15, wherein one treating substance is a sulphite.

37. (Previously Presented) Method according to claim 15, wherein one treating substance is an alcohol.

38. (New) Method according to claim 1, further comprising planning at least two sides having glue lines exposed to provide a first planed side and a second planed side facing opposite the first planed side, and applying said treating composition to both the first and second planed sides.

39. (New) Method according to claim 38, further comprising applying said treating composition simultaneously to both the first and second planed sides.

40. (New) Method according to claim 39, further comprising orienting the assembly so that the first planed side is facing upward and the second planed side is facing downward prior to applying said treating composition, and thereafter applying said treating composition to the first planed side by spraying and to the second planed side by roller coating.

41. (New) Method according to claim 1, wherein said treating composition is applied in an amount of from about 0.1 to about 100 g/m².

42. (New) Method according to claim 41, wherein said treating composition is applied in an amount of from about 1 to about 50 g/m².

43. (New) Method according to claim 42, wherein said treating composition is applied in an amount of from about 5 to about 30 g/m².

44. (New) Method according to claim 1, wherein said treating composition is applied from about 0.5 seconds to about 1 hour after planing.

45. (New) Method according to claim 44, wherein said treating composition is applied from about 0.5 seconds to about 1 minute after planing.

46. (New) Method according to claim 6, wherein said treating composition comprises about 10 to about 60 wt% urea and about 0.03 to about 2 wt% polyvinylalcohol in the form of an aqueous polyvinylalcohol dispersion.